## **Technical Information**

## Adhesin 114

ТҮРЕ	: Emulsion
PHYSICAL PROPERTIES	: Appearance : White Viscosity : $6500-8000 \text{ cps}$ (BF RVF $4/10/27^{\circ}$ C) Solids : $55 - 58 \%$ S.G. : $1.03 - 1.07$ pH : $4.0 - 5.0$ Flammability : Not flammable
OPERATING CONDITIONS	: Ready for use as supplied. Dilute with water if required. Direct transfer from brush, roller or glue spreader
SUGGESTED USES	: Case Sealing (varnish surface) It confirms to composition requirement of FDA regulations 21CFR 175.105 "Adhesives"
PRECAUTIONS	<ul> <li>Store in closed containers to prevent drying out and contamination.</li> <li>Rotate stock - first in - first out.</li> <li>Do not mix with other adhesives.</li> <li>Recommended to use the adhesive within 6 months.</li> </ul>
PACKAGE	: 50 Kg HDPE Drum / 200 kg MS drum

Henkel CAC Pvt. Ltd.

*Plot No. 1/1 Part 2, TTC Indl. Area, Thane Belapur Road, Koparkhairne, Navi Mumbai- 400710 Tel: +91-22- 27787371 Fax: +91-22-27780025* 



TDS-Adhesin 114 Page 1 Status: August 2010

Data is given as a guide to a products suggested use. Prospective users are strongly advised to undertake adequate tests under their own conditions on substrates to be used and with reference to the conditions of use of the final product before the above adhesive is adopted commercially. Any changes in these performance parameters should be preceded by similar tests