

# Technical Information

---

## Technomelt Tack 4533

<b>TYPE</b>	: Hot Melt
<b>PHYSICAL PROPERTIES</b>	: Appearance : Yellow Viscosity : Approx. 900 cps @ 180°C Approx. 1100 cps @ 170°C Approx. 1500 cps @ 160°C Approx. 2000 cps @ 150°C Approx. 2500 cps @ 140°C Softening point : 77 +/- 4°C Form : Block Storage Life : 12 months
<b>OPERATING CONDITIONS</b>	: Can be used in all standard nozzle applicatons. Running Temperature : 140 - 180°C Typical running temperature : 170°C Setting Speed : Fast
<b>SUGGESTED USES</b>	: Good for difficult varnished surfaces. Book binding application. It also conforms to composition requirements of FDA regulation 21 CFR 175.105 “ Adhesives”.
<b>PRECAUTIONS</b>	: Material is applied hot. Appropriate clothing and Gloves should be used. Keep containers and premelters covered to avoid contamination. Rotate stock-first in-first out
<b>PACKAGE</b>	:12 Kg PP Bag

### Henkel CAC Pvt. Ltd.

Plot No. 1/1 Part 2, TTC Indl. Area, Thane Belapur Road,  
Koparkhairne, Navi Mumbai- 400710  
Tel: +91-22- 27787371 Fax: +91-22-27780025

